

University of Groningen

New developments in the organic chemistry of fullerenes

Bellavia-Lund, C.; Hummelen, J.C.; Keshavarz, K.; Gonzalez, R.; Wudl, F.; Keshavarz-K., Majid

Published in:
Journal of Physics and Chemistry of Solids

DOI:
[10.1016/S0022-3697\(97\)00097-8](https://doi.org/10.1016/S0022-3697(97)00097-8)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1997

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Bellavia-Lund, C., Hummelen, J. C., Keshavarz, K., Gonzalez, R., Wudl, F., & Keshavarz-K., M. (1997). New developments in the organic chemistry of fullerenes. *Journal of Physics and Chemistry of Solids*, 58(11), 1983 - 1990. [https://doi.org/10.1016/S0022-3697\(97\)00097-8](https://doi.org/10.1016/S0022-3697(97)00097-8)

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.




NEW DEVELOPMENTS IN THE ORGANIC CHEMISTRY OF FULLERENES

CHERYL BELLAVIA-LUND, JAN-CORNELIS HUMMELEN, MAJID KESHAVARZ-K.,
ROSARIO GONZÁLEZ and FRED WUDL

Institute for Polymers and Organic Solids and Departments of Chemistry and Materials, University of California, Santa Barbara,
CA 93106-5090, USA

Since the discovery and isolation of macroscopic quantities of the fullerenes, the preparation of derivatives has grown rapidly over the last few years [1-3]. Functionalization of C_{60} in our group has been done primarily by cycloaddition reactions; particularly the 1,3-dipolar addition of diazoalkanes and alkyl azides.


temperature, the initially formed triazoline can be isolated in 35-40% yield. Thermolysis of the triazoline, followed by concomitant loss of nitrogen, gives rise to azafulleroids and fulleraziridines. Fulleraziridines and azafulleroids can also be obtained directly from C_{60} at higher reaction temperatures (160-180°C).




Unlike the addition of a second equivalent of diazoalkane to C_{60} , which does not show marked selectivity, the addition of azides to C_{60} shows chemo and regio selectivity [4]. Utilization of this unique selectivity, led us to the preparation of the first heterofullerene ' $C_{59}N$ ' in bulk quantity [5, 6]. Herein we report on its synthesis and mechanism of formation. We also describe the application of this procedure for the formation of higher heterofullerene analogs, i.e. ' $C_{69}N$ ' isomers [7] and introduce methodology that opens a viable route to the functionalization of azafullerenes [8].

The azafullerene ($C_{59}N$)₂ can be synthesized from C_{60} in three steps. The initial step in the formation of azafullerenes is the 1,3-dipolar cycloaddition of 2-methoxyethoxymethyl azide (MEM-azide) [9]. Not unlike the addition of diazoalkane, the addition of an alkyl azide to C_{60} occurs across the [6,6] bond. At room

temperature, when azide addition reactions are carried out at temperatures ranging from 60-140°C, in addition to the formation of azafulleroid and fulleraziridine a bisazafulleroid is formed and is the major product [4].




In an attempt to expand the scope of the chemo-selectivity of the azafulleroid other cycloadditions were performed. Taking advantage of the fullerenes as sensitizers, we showed that self-sensitized photo-oxygenation of [60]N-MEM azafulleroid afforded the cage-opened [60]N-MEM ketolactam in high yield [5].



In the course of characterizing the ring-opened cluster, FAB mass spectroscopy revealed a base peak at $m/z = 722$. The exact mass of this ion, 721.9991, was consistent with molecular formula $C_{59}N^+$. Further confirmation was found in the 'shrink-wrap' [10] fragmentation pattern: loss of CN, $m/z = 696$ followed by the successive loss of C_2 , m/z 672 and 648. Examination of the FAB mass fragmentation pattern of [60]N-MEM ketolactam to the azafullerene dimer $C_{59}N^+$ led us to propose the following mechanism (Scheme 1).

A relatively intense peak at $m/z = 780$ (95%) is due to loss of 2-methoxyethanol to yield the N-methyl carbonium ion, which is, in turn transformed to the four membered 1,3-oxazetidinium ring. The latter loses formaldehyde, followed by the loss of carbon monoxide to yield the azafullerene dimer.

We searched for a synthetic organic method that would mimic the events depicted previously to obtain macroscopic quantities of ' $C_{59}N$ '. A fast and remarkable reaction was observed when N-MEM ketolactam was treated with a large excess (15-20 equiv.) of pTsOH.H₂O



Scheme 1.

in *ortho* dichlorobenzene (ODCB) at reflux temperature under an atmosphere of nitrogen [6]. The color of the reaction mixture changed from red-brown to green-brown upon formation of a non-polar major product. After purification by HPLC, the latter (green in solution) was shown by cyclic voltammetry, ^{13}C -NMR, FTIR, UV-vis, elemental analysis and mass spectrometry (electrospray) to be the azafullerene dimer $(C_{59}N)_2$.

A strong argument for the dimer was obtained from the cyclic voltammogram, which showed three pairs of reversible one-electron reductions. The appearance of closely-spaced pairs of waves in CV suggested that our system consisted of two (identical) weakly interacting electrophores. The ^{13}C -NMR spectrum of $(C_{59}N)_2$ showed 29 lines in the region between 157 and 124 ppm. Other resonances (i.e. sp^3 hybridized carbon atoms) were not observed.

We were forced by the ^{13}C -NMR results to conclude that the [6,6]-open structure is a possible structure of the azafullerene, because the [6,6]-closed structure has an sp^3


hybridized carbon atom, ordinarily expected to appear in the region of maximally 50-101 ppm.

Having established its dimeric structure, we tried to rationalize this molecule's formation process. We proposed (Scheme 2) that the azafullerene dimer is formed first in a manner that mimics the gas-phase formation of azafullerene, i.e. that the acid protonates the MEM moiety, inducing the loss of 2-methoxyethanol, followed by rearrangement to the azafullerene dimer. In the presence of the 2-methoxyethanol (or water) the azafullerene dimer can be reduced to the azafullerene radical. Finally, the radical dimerizes to yield $(C_{59}N)_2$.


To corroborate the proposed mechanism for the formation of the azafullerene $(C_{59}N)_2$, we carried out the reaction in the presence of nucleophiles to trap the proposed carbonium ion intermediates [11]. This led to the isolation of new holey balls, fullerenes with a ring larger than a hexagon, as depicted in Scheme 3.

In the presence of excess p-toluenesulfonic acid monohydrate and hydroquinone, a stronger reducing agent than the 2-methoxy ethanol, in ODCB at 170-180°C, the ketolactam was converted to the desired hydroazafullerene as shown in Scheme 4 [11].

From the number of carbon resonances in the sp^2



Scheme 2.

(a) pTsOH H₂O, Hexanoic acid, ODCB, 180 C, 35%(b) pTsOH H₂O, Hydroquinone, ODCB, 180 C, 50%(c) TiCl₄, CH₂Cl₂, ODCB, 25 C, 47%

Scheme 3.



previously stated, the ¹³C NMR of the latter does not show a signal in the sp³ region.


As part of our continued interest in the azafullerenes, we have initiated studies to prepare derivatives [8]. A principal reason for derivatization of C₅₉N was to glean information on the variability of the chemical shift of the sp³ carbon atoms as a function of substitution.

According to theoretical calculations [12] the inter-dimer bond of (C₅₉N)₂ is relatively weak (18 kcal/mol) and should, under photolysis or thermolysis conditions, undergo facile homolysis. We achieved derivatization of C₅₉N by thermolytic dissociation of the inter-dimer bond of (C₅₉N)₂, followed by free radical reaction with a good hydrogen atom donor, diphenylmethane.


Treatment of (C₅₉N)₂ with excess diphenylmethane in refluxing ODCB for 48 h afforded, upon chromatographic purification, one product. This was shown to be the substituted azafullerene C₅₉(CHPh₂)N by ¹H and ¹³C NMR, FTIR, UV-vis, mass spectrometry, and cyclic voltammetry. The heterofullerene was obtained in 42% isolated yield after HPLC purification, demonstrating the

region (28) and a signal in the sp³ region (72.1 ppm), the hydroazafullerene was assigned to the closed structure with C₈ symmetry, as shown below.

Azafullerene C₅₉HN is green in common solvents and its UV-VIS spectrum is virtually identical to that of (C₅₉N)₂. Because the electronic absorption of C₅₉HN and (C₅₉N)₂ are the same and the NMR data confirms the closed structure for C₅₉HN, the closed-closed structure was also assigned to (C₅₉N)₂ as well; even though, as




Scheme 4.




relatively clean conversion of $(C_{59}N)_2$ to a stable soluble derivative in good yield (4).

In the course of the reaction, formation of $C_{59}HN$ was



expected to be a dominant feature, however it was only 2% of the reaction mixture. A plausible explanation was that $C_{59}HN$, similar to $(C_{59}N)_2$, undergoes a free radical

UV-vis data demonstrated that the electronic structure of all three molecules is essentially identical. The ^{13}C NMR spectrum of $C_{59}(CHPh_2)N$ revealed a similar pattern in the sp^2 region to that of its precursors and an unmistakable sp^3 carbon at 86.1 ppm, in agreement with a 'closed' structure. This carbon resonance is down-field shifted by 14 ppm relative to the sp^3 carbon of $C_{59}HN$ [11], as expected on going from hydrogen to alkyl substitution. ^{15}N NMR studies done on these compounds allowed assignment **a** of carbons **b**, to the nitrogen atom [13]. After, optimization for a long T_1 , the ^{13}C NMR of $(C_{59}N)_2$




reaction to afford $C_{59}N\bullet$ (equation 5, above).

In a control experiment, treatment of $C_{59}HN$ with diphenylmethane in refluxing ODCB for 24 h, afforded, upon chromatography (silica gel, toluene) $C_{59}(CHPh_2)N$ in good yield as well as trace amounts of $(C_{59}N)_2$ and unreacted $C_{59}HN$. This study shows that $C_{59}HN$ can also undergo homolytic cleavage to yield the $C_{59}N\bullet$ radical,

revealed an sp^3 carbon resonance at 90.3 ppm, corresponding to its inter-dimer carbon. This finally confirmed the closed structure as depicted below and illustrated the expected increase in chemical shift with increasing electronegativity of the substituent on the sp^3 center.

In an attempt to expand the scope of the heterofullerene family, we initiated similar studies with C_{70} [7]. Unlike




where all three species $C_{59}N\bullet$, $C_{59}HN$ and $(C_{59}N)_2$ are involved in the process leading to $C_{59}RN$.

Full characterization of the adduct showed remarkable similarities to $(C_{59}N)_2$ and $C_{59}HN$, in particular the

the transformation of C_{60} (I_h) to $C_{59}N$, C_{70} (D_{5h}) with its five different types of carbon atoms (see 'a'-'e' above) could, following the same strategy as describe previously, give rise to five distinct $C_{69}N\bullet$ isomers.

Simultaneous formation of all five radicals could lead to the formation of up to 15 different $C_{69}N$ dimers! With the synthesis outlined before for the formation of [60]azafullerenes and a solid understanding of the mechanism of formation we sought a selective synthesis of $(C_{69}N)_2$ isomers [14].

Similar to C_{60} , cycloaddition to C_{70} occurs across the [6,6] bond [7, 15-19] giving rise to a minimum of four possible isomers. The 1,3-dipolar addition of azide could, in principle, give rise to a maximum of six triazoline isomers, where addition across a [6,6] bond between two different types of carbon atoms gives rise to a pair of regioisomers, as depicted in Scheme 5 [15, 20].



At moderate temperatures the addition of MEM-azide to C_{70} gives rise to three triazoline isomers, where addition occurs to a greater extent across the [a,b] bond, the bond with greatest curvature, with preferential formation of **1**. Addition across the lower strain [c,c] bond also occurs but to a lesser extent, producing **3** (**6**).

In accord with theory [21], structures $C_{1(d,e)}$, $C_{1(c,e)}$ and $C_{5(e,e)}$ (Scheme 5) are not observed. Also, by the same principle, azafulleroid **8** (below) is not observed. At 55°C triazoline **3**, a chemoisomer of regioisomers **1** and **2**,


carbon atoms are pyramidal and introduction of sp^3 carbons in the poles is expected to alleviate some of the polar strain of the C_{70} cluster.

After separation of **1** and **2** by preparative HPLC, each was subjected to thermolysis. A dilute toluene solution of each isomer was heated to 80°C until the disappearance of the triazoline was observed by TLC [(8) and (9)]. In each case **1** or **2** gave rise to three separable bands by column chromatography (silica gel, toluene): C_{70} (64%), azafulleroid **5** or **6** (23%), respectively, and aziridine **4** (5%).

When MEM-azide addition was carried out at a higher temperature (180°C), the preference of addition across

the bond containing the greatest local curvature (a-b) (reflected in formation of **4**), as opposed to addition across the bond with the shortest bond order (c-c) (reflected in formation of **7**), decreased from 4:1 to 3:2.

This result reflects that: (1) at this temperature the MEM-azide also decomposes to MEM-nitrene which is expected to exhibit lower selectivity due its higher energy content; and (2) at a more elevated temperature the selectivity of the 1,3-dipolar addition is also expected to decrease. This study was the first step towards a full




was readily and selectively transformed to azafulleroid **6** and aziridine **7** as well as a small quantity of C_{70} , whereas **1** and **2** remained intact, showing the varied stability of the isomers.


In comparing the thermal stability of **1**, **2** and **3**; the reduced stability of **3** is very likely due to the higher strain in its polar region; i.e. **1** and **2**, have a lower total strain energy than **3** because in the former, two of the polar

understanding of addition of azide to C_{70} and allowed for easy characterization of the subsequent transformation to azafulleroids. The addition of MEM-azide to C_{70} showed a wider range of selectivity than previously reported reactions of C_{70} such as osmylation [18] and addition of diazomethane [15].

Once we had a handle on the structures of the two [70] azafulleroids, we subjected each to photo-oxygenation.



We first investigated the cage opening transformation of azafulleroid **6**. Due to its C_s symmetry, **6** afforded a single




ketolactam isomer **9** upon a 2 + 2 addition of singlet oxygen, followed by decomposition of the 1,2-dioxetane intermediate. The structure of **9** was determined by FTIR, NMR and mass spectroscopy.

Similar to its [60]analog, the FAB mass spectrum of **9** revealed a base peak at $m/z = 842$, consistent with $C_{69}N^+$ [22]. Examination of the conversion of **9** to $C_{69}N$ suggests that only one $C_{69}N$ isomer should be formed, the [70]azafullerene where carbon 'a' is replaced by the nitrogen atom (Scheme 6).

going from C_{60} to $(C_{59}N)_2$ the retention time increases from 7 to 15 min. It is reasonable that the conversion of C_{70} to $(C_{69}N)_2$ would increase the retention time from 15 to 34 min. Electrospray analysis confirmed this, showing a molecular ion at $m/z = 1685$ and a strong base peak at $m/z = 842$. The ^{13}C NMR revealed 29 peaks in the sp^2 region, illustrating the high symmetry of the isomer. Due to the low solubility of the dimer and the tendency for sp^3 carbons adjacent to nitrogen to have long T_1 times, no resonances in the sp^3 region were found above the noise level.

Unlike **6**, azafulleroid **7** has C_1 symmetry, where photooxygenation could occur across the [a,b] bond or the [c,c] bond giving rise to two distinctly different ketolactam isomers. HPLC and 1H NMR revealed the presence of two isomers in 4:1 ratio, both with C_1 symmetry. As we and other groups have demonstrated, addition reactions to C_{70} (at moderate temperatures) occur preferably across the [a,b] bond; designating **11** as the major product (Scheme 7).


Analysis of the decomposition of the ketolactam isomers **11** and **12** is shown below. In both cases the



The stage was now set to chemically generate $C_{69}N$. Treatment of ketolactam **9** with an excess of pTSAH in refluxing ODCB produced a single apolar product **10** [19] as determined by HPLC; retention time 34 min (11).

This observation suggested that we had isolated the $C_{69}N$ as its dimer. This is based on the premises that on


mechanism suggests that each ketolactam isomer should give rise to a different $(C_{69}N)_2$ isomer; where decomposition of **11** leads to the exchange of carbon 'b' for nitrogen (Scheme 8(a)) and decomposition of **12** leads to exchange of carbon 'c' (Scheme 8(b)). Interestingly, the symmetry of **13** and **14** are different, allowing for the



Scheme 5.


distinction of the two dimers as well as their ketolactam precursors.

After isolation and complete characterization of **11**, we subjected it to the acidic conditions described above for the conversion to (C₆₉N)₂. The electronic spectrum of the



Scheme 7.


In this paper we have reviewed the three step synthesis for the conversion of C₆₀ to its heterofullerene analog C₅₉N. Postulation of a series of transformations in the gas phase leading to the formation of C₅₉N⁽⁺⁾ was the basis for experiments that led to the synthesis of bulk quantities of the azafullerene dimer. Not unexpectedly, the inter-cluster bond of the dimer is relatively weak (18 kcal/mol) [12] and ready for homolysis which led us to exploit a homolytic approach to achieve derivation of the azafullerene cage by a free radical process. The ease of synthetic incorporation of a nitrogen atom into the




apolar product, after separation from pTSAH, was very similar to (C₆₉N)₂ isomer **10**; however HPLC revealed a single peak with a retention time of 41 min, 7 min longer than **10**.

¹³C NMR of **13** was also similar to that of **10** revealing ~30 carbon resonances in the sp² region. Efforts to prepare and fully characterize **14** are in progress.

fullerene skeleton had another important consequence; it provided the tool necessary to correctly assign the chemical shift of carbon atoms **a** and **b** to the heteroatom in (C₅₉N)₂, C₅₉HN and C₅₉(CHPh₂)N through a combination of ¹³C NMR and ¹⁵N-coupled ¹³C NMR spectroscopy. Finally, realization that a fullerene sp³ carbon atom bonded to nitrogen can have its T₁ relaxation



Scheme 6.



Scheme 8.

changed drastically was a key observation to help locate the missing inter-cluster carbon atoms at 90.3 ppm. This provided unequivocal proof that (C₅₀N)₂ has a [6,6]closed structure.

Lastly, we were very pleased to discover that the above methodology is applicable to the conversion of C₇₀ to C₆₉N and found that three out of the five possible C₆₉N dimers can be formed selectively from their corresponding holey balls. In conclusion, we have discovered a general synthesis of azafullerenes which can be summarized as:

FULLERENE → AZAFULLEROID

→ HOLEY BALL → AZAFULLERENE

Acknowledgements - We thank the National Science Foundation for support through the Materials Research Science and Engineering Center as well as individual investigator grant DMR-9500888. Rosario González thanks the Ministerio de Educación y Ciencia (Spain) for a postdoctoral fellowship.

REFERENCES

- Haddon, R. C., *Science*, 1993, **261**, 145-155.
- Hirsch, A., *The Chemistry of the Fullerenes*. Thieme, Stuttgart, 1994.
- Taylor, R., *The Chemistry of Fullerenes*. World Scientific, Singapore, 1995.
- Grösser, T., Prato, M., Lucchini, V., Hirsch, A. and Wudl, F., *Angew. Chem.*, 1995, **107**, 1462.
- Hummelen, J. C., Prato, M. and Wudl, F., *J. Am. Chem. Soc.*, 1995, **117**, 7003-7004.
- Hummelen, J. C., Knight, B., Pavlovich, J., González, R. and Wudl, F., *Science*, 1995, **269**, 1554.
- Bellavia-Lund, C. and Wudl, F., *J. Am. Chem. Soc.*, 1997, **119**, in press.
- Bellavia-Lund, C., González, R., Hummelen, J. C., Hicks, R. G., Sastre, A. and Wudl, F., *J. Am. Chem. Soc.*, 1997, **119**, 2946.
- Prato, M., Chan Li, Q., Wudl, F. and Lucchini, V., *J. Am. Chem. Soc.*, 1993, **115**, 1148-1150.
- O'Brien, S. C., Heath, J. R., Curl, R. F. and Smalley, R. E., *J. Chem. Phys.*, 1988, **88**, 220.
- Keshavarz-K., M., González, R., Hicks, R. G., Srdanov, G., Srdanov, V. I., Collins, T. A., Hummelen, J. C., Bellavia-Lund, C., Pavlovich, J. and Wudl, F., *Nature*, 1996, **383**, 147-150.
- Andreoni, W., Curioni, A., Holczer, K., Prassides, K., Keshavarz-K., M., Hummelen, J.-C. and Wudl, F., *J. Am. Chem. Soc.*, 1996, **118**, 11335-11336.
- Bellavia-Lund, C., Collins, T. and Wudl, F., *J. Am. Chem. Soc.*, 1997, **119**, in press.
- Bellavia-Lund, C. and Wudl, F., manuscript in preparation.
- Smith III, A., Strongin, R., Brard, L., Furst, G., Romanow, W., Owens, K. and Goldschmidt, R., *J. Am. Chem. Soc.*, 1995, **117**, 5492-550 and references therein.
- Meier, M., Poplawski, M., Compton, A., Shaw, J., Selegue, J. and Guarr, T., *J. Am. Chem. Soc.*, 1994, **116**, 7044-7048.
- Seiler, P., Herrmann, A. and Diederich, F., *Helv. Chim. Acta.*, 1995, **78**, 344-354.
- Hawkins, J. M., Meyer, A. and Solow, M. A., *J. Am. Chem. Soc.*, 1993, **115**, 7499.
- A different preparation of (C₆₉N) appeared recently while this work was in progress: Nuber, B. and Hirsch, A., *J. Chem. Soc. Chem. Commun.*, 1996, 1421.
- Hassner, A. J., *J. Org. Chem.*, 1968, **33**, 2684.
- Henderson, C. C., Rohlfing, C. M., Gillen, K. T. and Cahill, P. A., *Science*, 1994, **264**, 397.
- For another report of C₆₉N in the gas phase see: Lamparth, I., Nuber, B., Shick, A., Skiebe, T., Grosser, T. and Hirsch, A., *Angew. Chem., Int. Ed. Engl.*, 1995, **35**, 2257-2258.